

# *PermaWrap™*

## Composite FRP Sleeve

(Part Numbers: P04-6 thru P60-18)

### Description

The PermaWrap™ Composite FRP Sleeve is a rigid coil-shaped device used in conjunction with the WrapMaster's – Adhesive & Putty systems to restore hoop-strength to degraded carbon steel piping. The PermaWrap™ Sleeve is constructed from high tensile strength fiberglass strands incorporating a “magnetically detectable” material for Smart Pig Detection. The composite laminate is impregnated with a chemically resistant polyester resin and has a functional “male and female” surface of embossment. The “Diamond Lock” feature adds to the robustness of the PermaWrap™ Sleeve by providing a Dual Locking System - mechanical locking in addition to securing the system with the WrapMaster's Adhesive.

**Recommended Repair Types:** “Blunted” defects associated with corrosion, dents or gouges with up to 80% wall loss on carbon steel piping. For use on ductile steel pipe for pipe grades up to API-5LX-80. Permanently repair of external defects. For use on field bends with a 5R minimum bend radius and the repair of corrosion defects associated with a Girth Weld. Temporarily repair internal defects – longevity may be determined by the internal metal loss rate.

### Features

High Tensile Strength	Superior chemical resistance
Magnetically Detectable	Low Elongation
Dual Locking System	Excellent Durability

### Typical Properties

Tensile Strength	90 ksi	ASTM D3039
Tensile Modulus	5.0 msi	
Transverse Tensile Strength	12.0 ksi	ASTM D3039
Tensile Elongation (%)	1%	ASTM D638
Layer Thickness	.060 - .075	
Number of Layers	8	
Configured for Pipe Size(s)	4” thru 60”	
Standard Sleeve Widths	6”, 9”, 12”, 15” and 18”	
Max Operating Temperature	225°F / 107°C	ASME PCC-2



### Applying

WrapMaster's Installer Certification required for product use. Basic outline of application steps are 1) Pipe surface area should be clean, dry and free of contamination with an anchor pattern (NACE #3 or SA-2 1/2). 2) Use Putty to fill cavity and tented areas. 3) Apply Adhesive to pipe surface. 4) Attach PermaWrap™ Composite FRP Sleeve and apply adhesive while wrapping sleeve around pipe. 5) Tighten Sleeve and allow to cure for 2 hours.

### Storage

PermaWrap™ Composite FRP Sleeve should be stored in a dry shaded place at room temperature (77 °F).

---

**DISCLAIMER:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. Including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data is subject to change as WrapMaster deems appropriate. Appropriate engineering controls and precautions to be observed in using the material.

# Wrapmaster™ Adhesive System

## Description

Wrapmaster's Adhesive is a highly thixotropic, two component, epoxy adhesive system. This adhesive forms a resilient bond and maintains its strength over a wide range of temperatures. Wrapmaster's adhesive is suitable for bonding a variety of substrates with minimal surface preparation.

**Recommended Substrates:** PVC, polycarbonate, acrylic, aluminum, epoxy coated metal, ABS, carbon and stainless steel, and FRP.

## Features

Non-sagging gaps filled to 1inch	Superior impact and peel strength
Little or no surface preparation	Offers excellent tolerance to off-ratio mixing
Rapid room temperature cure 100% reactive	Excellent environmental resistance

## Typical Properties

Tensile Lap Shear @ 77 °F	2,500-2,700	ASTM D1002
Tensile Lap Shear @ 180 °F	1,800-2,000	ASTM D1002
Tensile Elongation (%)	25-35	ASTM D638
Peel Strength (pli)	60	ASTM D3167
Shore A Hardness	10-15	
Bondline Thickness	.005-1.00	

## Applying

Bonding surface should be clean, dry, and free of contamination. Extensive surface preparation is not required for the Wrapmaster system, a light scuffing with 100 grit sand paper or scotch bright pad and a solvent wipe. To assure maximum bond strength, surfaces must be mated within the adhesive's open time. Use enough material to completely fill the joint when parts are clamped.

## Storage

Adhesives should be stored in a cool, dry place when not used for a long period of time. The shelf life is one year from the date of manufacture when stored in a climate-controlled environment. Exposure above room temperature will reduce shelf life.

---

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. Including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data is subject to change as WrapMaster deems appropriate. Users should review the Material Safety Data Sheet (MSDS) for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the MSDS are available upon request.

## *... Limitation of Warranty...*

1. All products are sold subject to Terms and Conditions of Sale by WrapMaster, Inc. A copy of these terms and conditions is available from the company at its office in Longview, Texas. All products are sold F.O.B. WrapMaster plant.
2. WrapMaster warrants that upon shipment, the goods will be (i) free from defects and workmanship and (ii) substantially in accordance with WrapMaster's standard specifications for the specific goods. If, within sixty (60) days after shipment, WrapMaster receives written notice of any defect in the material or workmanship of the specified goods, or the failure of the goods to meet WrapMaster's standard specifications therefore, WrapMaster will correct each such defect of failure, at WrapMaster's option, by either making available repaired goods or replacement goods.
3. All goods must be handled, stored, transported, installed, operated and maintained in accordance with WrapMaster's standard written instructions set forth herein or provided or approved in writing by WrapMaster. WrapMaster makes no warranties which extend to damage to the goods due to deterioration or wear occasioned by sunlight, chemicals, abrasion, corrosion, installation, operation or maintenance, abnormal conditions or temperature or other use of the goods above standard recommended uses or in an improper manner. WrapMaster's sole responsibility for defects in material and workmanship or goods and Customer's sole remedy hereunder will be as stated in Terms and Conditions of Sale of WrapMaster, Inc. Composite Systems are UV sensitive.
4. WRAPMASTER, IT'S SUBCONTRACTORS AND SUPPLIERS MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, AND SPECIFICALLY DISCLAIM ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR CONFORMITY WITH SAMPLES.
5. WRAPMASTER WILL NOT BE LIABLE FOR INCIDENTAL, INDIRECT, SPECIAL OR CONSEQUENTIAL DAMAGES, OR FOR LOST PROFITS, SAVINGS OR REVENUES OF ANY KIND, WHETHER OR NOT WRAPMASTER HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.
6. INSTALLATION OF WRAPMASTER PRODUCTS BY ANYONE OTHER THAN A CERTIFIED INSTALLER WILL VOID ANY AND ALL WARRANTIES SET FORTH HEREIN, IS DANGEROUS AND MAY CONSTITUTE A VIOLATION OF APPLICABLE GOVERNMENTAL REGULATIONS.